

	广西金桂浆纸业有限公司 GUANGXI JINGUI PULP&PAPER CO.,LTD.	文件编号 Document number	JG-28200-PSP-050
		生效日期 2.0版 Effective date	2022-01-10 Jan. 10, 2022

单面涂布白卡 IVJ

C1S IVORY BOARD (Ningbo Fold)

指标 Technical Information	单位 Unit	公差 Margin	标准 Target														检验方法 Test Method
定量 Basis Weight	g/m²	±3%	170	180	190	200	210	220	230	250	270	280	300	325	350	400	ISO 536 GB/T 451.2
	24"x36" 500 (Ib)		104	111	117	123	129	135	141	154	166	172	184	200	215	246	
厚度 Thickness	µm	±3%	212	227	242	257	272	290	310	340	370	385	415	460	490	555	ISO 534 GB/T 451.3
	pt		8.3	8.9	9.5	10.1	10.7	11.4	12.2	13.4	14.6	15.2	16.3	18.1	19.3	21.9	
泰伯挺度(15°)CD Taber Stiffness	mN•m	目标值 target	1.76	1.94	1.94	2.24	2.65	2.94	3.76	4.82	5.88	7.18	8.47	10.6	11.8	16.5	ISO 2493 GB/T 22364
		最小值 min	1.50	1.65	1.65	1.90	2.25	2.50	3.20	4.10	5.00	6.10	7.20	9.00	10.0	14.0	
泰伯挺度(15°)MD Taber Stiffness	mN•m	目标值 target	2.47	3.00	3.76	4.59	5.06	6.47	7.65	9.18	10.4	11.8	15.3	20.6	22.9	29.4	
		最小值 min	2.10	2.55	3.20	3.90	4.30	5.50	6.50	7.80	8.80	10.0	13.0	17.5	19.5	25.0	
水分 Moisture	%	±1.0	7.0														ISO 287 GB/T 462
PPS 粗糙度-正面 PPS Roughness-top	µm	≤	1.50														ISO 8791-4 GB/T 22363
亮度-正面 Brightness D65/10 - top	%	±2.0	90.0														ISO 2470-2 GB/T 7974
光泽度 75°-正面 Gloss-top	%	≥	35														TAPPI 480 GB/T 8941
IGT 干拉毛-正面 IGT Picking-top	m/s	≥	1.20														ISO 3783 GB/T 22365
Cobb 值 60s -正面 Cobb 60s-top	g/m²	≤	55.0														ISO 535 GB/T 1540
层间结合强度 Scott Plybonding	J/m²	≥	130														TAPPI 569 GB/T 26203
偏斜度-平张 Squareness	mm	≤	2.0														GB/T 451.1
尺寸偏差-平张 Size Deviation	mm	≤	2.0														

测试条件：温度 (23±1) °C/ 湿度 (50±2) % (参考标准 GB/T10739 & ISO 187)

Test climate 23°C/50%RH (according toGB/T10739 & ISO 187)